

VESTODUR®

Polybutylene terephthalate compounds

Evonik manufactures a range of polybutylene terephthalate compounds that are supplied under the registered trademark VESTODUR®. Material properties characterizing VESTODUR® compounds are:

- high thermostability
- high stiffness
- low water absorption resulting in high dimensional stability
- high hardness
- good strength
- good sliding friction behavior, low abrasion
- good creep behavior
- good electrical properties
- good chemical resistance
- good weathering resistance
- good processability
- no tendency to form stress cracks

Customized portfolio

By adding various additives into virgin PBT, its properties can be adjusted to meet the requirements of different applications:

- Stabilizers prevent damage during further processing and increase durability upon exposure to UV, heat, and moisture.
- Processing aids facilitate demolding.
- Polymer modifications improve flexibility and impact strength and reduce post shrinkage.
- Flame-retardant additives permit the production of self-extinguishing resins.
- Fillers and reinforcing agents increase stiffness and dimensional stability upon exposure to heat. Chopped strands have proven most effective in this regard. Minerals and micro glass beads counteract the tendency to warp.
- Special properties, such as laser markability, metallizability, and different electrical conductivities can be adjusted through special additives.

Long-term properties of PBT under load

At elevated temperatures, thermoplastics begin to flow or creep under the influence of stresses, especially when they are unreinforced. PBT has a relatively low tendency to creep, but the designer must still take creep resistance into consideration because it declines under continuous load in comparison with short-time stability. On the other hand, this also means that the initial stress will drop when the strain is held constant. Ten thousand hours worth of readings have been made for many VESTODUR® compounds. Details and data can be obtained from your contacts.

Resistance to heat, radiation, and chemicals

The proper stabilizers must be incorporated into thermoplastics to give them the resistance needed for long-term use in harsh environmental conditions (UV radiation, hot air, etc.).

Heat aging

Heat stabilizers greatly improve the aging behavior of polybutylene terephthalate, making it possible to use it longer at high temperatures. With the exception of a few special base products, all VESTODUR® resins come with an optimized stabilizer system. For data concerning heat aging please ask your contacts.

A range of VESTODUR® compounds has also been classified according to UL standard 746B for the relative temperature index TI. In this case, TI characterizes the creep resistance for approximately 60,000 hours. Details can be found in the special product brochure "Underwriters Laboratories (UL) Certifications for High Performance Polymers from Evonik Industries AG".

Hydrolysis resistance

PBT is a polycondensate, a class of polymers that only have limited resistance to moist air at higher temperatures. The most important application of PBT is fiber optic jacketing. Since more and more cables are being installed in environments that feature high temperatures and high humidity, it became necessary to develop PBT compounds with improved hydrolytic stability, resulting in the resins VESTODUR® 3010, 3013 und 3030.

UV resistance

When a polymer is exposed to light of short wavelengths below 400 nm its molar mass declines rapidly. Moldings and semi-finished products become brittle. Light-stability agents, UV absorbers and radical interceptors can greatly reduce the damage caused by weathering. Suitable types of carbon black offer the best protection of all, provided that the resulting black coloring is considered acceptable. Although light-stability agents and UV stabilizers substantially improve weathering resistance, they are not as effective as carbon black. The addition of pigments can serve to stabilize as well as sensitize. Nevertheless, pigments or blacks may also affect a polymer's mechanical properties.

Chemical resistance

PBT is extremely resistant to stress cracks induced by chemicals. For details please you're your contacts or can be obtained from the list next page.

Abrasion and frictional behavior

Polybutylene terephthalate is distinguished by very high abrasion resistance. This can be determined according to DIN 53754 (Taber) or DIN 53516. The test consists of abrasion from emery grinding. Harder resins have a higher abrasion than softer resins. The abrasion only increases again for very soft resins.

For bearings or sliding parts, the coefficient of sliding friction is more important than abrasion. This coefficient is a function of pressure per surface area of bearing, friction velocity, surface structure and surface hardness of the friction partner, and temperature. It is low for PBT. The addition of reinforcing agents or fillers (glass fibers, graphite) doesn't affect sliding friction or abrasion provided that the surface skin of the molding hasn't been damaged. The influence of the additives is only evident (in the case of glass fibers) from the increased abrasion of the sliding partners, which only occurs after the additives have come to the surface.



Lubricants influence the abrasion and frictional behavior. The lubrication greatly reduces the coefficient of friction and almost stops abrasion completely. PBT's high chemical resistance permits the use of nearly any lubricant.

Physiological and toxicological analysis of VESTODUR® resins

Please direct all questions on the toxicological properties of VESTODUR® compounds and relevant analysis pertaining their contact with foodstuffs to the indicated contact address. Here you will also receive the up-to-date safety data sheets of VESTODUR®.

Applications

VESTODUR® compounds can be used for a wide range of applications, for example, for thin-walled injection-molded parts in electrical engineering applications, for especially dimensionally stable components of high surface quality in the automotive industry, as a barrier layer in multilayer fuel lines, for laser-markable components, and in the cable industry. High-molecular extrudable VESTODUR® specialty products have come to occupy a leading position as materials for secondary fiber optic jacketing, because they fulfil the requirements perfectly.



Chemical resistance of PBT compounds

Chemicals	VESTODUR® unreinforced			VESTODUR® reinforced/filled		
	23°C	60°C	80°C	23°C	60°C	80°C
Acetic acid 5%/10%/100%	+ / + / ~	~ / ~ / ~	- / - / -	+ / + / ~	~ / ~ / ~	- / - / -
Acetone	+	-		~	-	
Ammonium hydroxide 10%	~	-	-	~	-	-
Brake fluid	+	+	~	+	+	~
Calcium chloride 10%	+	+	-	+	~	-
Chloroform	-	-		-	-	
Diesel oil	+	+	+	+	+	+
Dioxane	+	-		+	-	
Ethanol	+	~	-	+	~	-
Glycol	+	~	-	+	~	-
Hydraulic oil	+	+		+	+	
Hydrochloric acid 10%/37%	+ / -	~ / -	- / -	+ / -	~ / -	- / -
Hydrofluoric acid 5%	+	~	-	-	-	-
Isopropanol	+	~		+	~	
Motor oils	+	+	~	+	+	~
Octane	+	+	+	+	+	+
Paraffin oil	+	+	+	+	+	+
Petrol, super	+	+	~	+	+	~
Petroleum	+	+	+	+	+	+
Petroleum jelly	+	+	+	+	+	+
Potassium chloride 10%	+	+	-	+	~	-
Sea water	+	+	-	+	+	-
Silicone oils	+	+	+	+	+	+
Soap solution	+	+	-	+	-	-
Sodium chloride 10%	+	+	-	+	~	-
Sodium hydroxide 1%	+	~	-	-	-	-
Transformer oil	+	+	+	+	+	+
Turpentine	+			+		
Vegetable oils	+	+	+	+	+	+

+ = resistant, no or only slight weight change

~ = resistant within limitations, short-term contact with the agent possible

- = unstable, weight change over 5%, marked decline in mechanical properties

Mechanical and thermal properties of VESTODUR® compounds and fire behavior

Properties	Test method	Unit	VESTODUR®			VESTODUR®		
			1000	2000	3000 series*	HI19	X4877	
Density	23 °C	ISO 1183	g/cm ³	1.31	1.31	1.31	1.26	1.49
Melting range	DSC	ISO 11357	°C	221 –226	221 –226	221 –226	200 –205	200 –205
Melt volume flow rate ¹⁾	250 °C/2.16 kg	ISO 1133	cm ³ /10 min	45	14	9	12	20
Heat deflection temperature under load								
Method A	1.8 MPa	ISO 75	°C	55	55	55	50	175
Method B	0.45 MPa		°C	150	150	150	110	195
Vicat softening temperature		ISO 306						
Method A	10 N		°C	220	220	220	190	190
Method B	50 N		°C	180	180	180	125	165
Coefficient of linear expansion	23–55°C	ISO 11359						
	in flow direction		10 ⁻⁴ K ⁻¹	1.1	1.1	1.1	1.5	0.5
	in transverse direction		10 ⁻⁴ K ⁻¹	1.1	1.1	1.1	1.5	
Oxygen index		ISO4589	%	23	23	23		
Flammability acc. UL94	0.4 mm 0.8 mm 1.6 mm	IEC 60695		HB HB	HB HB	HB HB	HB HB	HB HB
Glow wire test	wall thickness = 2mm	ISO 60695–2-12/-13						
GWFI			°C	800	800	800	750	750
GWIT			°C	800	800	800	750	750
Water absorption	23 °C, saturation	ISO 62	%	0.45	0.45	0.45	0.35	0.25
Mold shrinkage ²⁾		ISO 294-4, Processing						
	in flow direction	ISO 1874-2	%	1.5	1.6	1.7	1.4	0.3
	in transverse direction		%	1.5	1.6	1.7	1.4	1.0
Tensile test	testing speed 50 mm/min	ISO 527-1/-2						
Stress at yield			MPa	55	55	55	27	105
Strain at yield			%	4	7	9	23	5
Strain at break			%	>50	>50	>50	>50	5.5
Tensile test	testing speed 50 mm/min	ISO 527-1/-2						
Tensile strength			MPa					
Strain at break			%					
Tensile modulus		ISO 527-1/-2	MPa	2600	2600	2600	550	5200
Ball indentation hardness H 30		ISO 2039-1	N/mm ²	160	150	150	50	105
Shore hardness D		ISO 868		79	77	77	65	79
CHARPY impact strength	23 °C –30 °C	ISO 179/1eU						
			kJ/m ²	200 C	N	N	N	80 C
			kJ/m ²	185 C	300 CN	300 C	N	70 C
CHARPY notched impact strength	23 °C –30 °C	ISO 179/1eA						
			kJ/m ²	5.0 C	7.0 C	7.0 C	30 C	18 C
			kJ/m ²	4.5 C	6.0 C	6.0 C	8.0 C	13 C

N = no break, C = complete break

* Series consists of VESTODUR® 3000, 3001, 3010, 3013, 3030

¹⁾ Moisture content < 0.05 %

²⁾ Pigmentation can change mold shrinkage.

Electrical properties of VESTODUR® compounds

Properties*	Test method	Unit	VESTODUR®			VESTODUR®	
			1000	2000	3000 series*	HI19	X4877
Comparative tracking index Test solution A CTI 100 drops value	IEC 60112		600 575	600 575	600 575	600 575	600 575
Volume resistivity 23 °C	IEC 60093	Ω cm	10 ¹⁵	10 ¹⁵	10 ¹⁵	10 ¹⁵	10 ¹⁴
Surface resistance 23 °C	IEC 60093	Ω	10 ¹³	10 ¹³	10 ¹³	10 ¹³	10 ¹³
Relative permittivity 23 °C, 100 Hz 23 °C, 1 MHz	IEC 60250		3.3 3.5	3.3 3.5	3.3 3.5	4 3.6	4.7 4.5
Dissipation factor 23 °C, 100 Hz 23 °C, 1 MHz	IEC 60250		0.002 0.023	0.002 0.023	0.002 0.023	0.022 0.033	0.02 0.03
Electrolytic corrosion	IEC 60426	step	A1	A1	A1	A1	A1
Electric strength ¹⁾ K 20/P 50	IEC 60243-1	KV/mm	27	27	27	27	27

*Pigmentation may change electrical values.

¹⁾ Determined in transformer oil ($\epsilon_r \approx 2.2$) at 1 mm injection molded sheets.

Contacts

Automotive

Frank Lorenz
frank.lorenz@evonik.com

Electronics

Frank Zelder
frank.zelder@evonik.com

Cable industry

Holger Renners
holger.renners@evonik.com

Americas

Kevin Bonhoff
kevin.bonhoff@evonik.com

Asia/Pacific

Dr. Simon Ting
simon.ting@evonik.com

® = registered trademark

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

www.vestodur.com

Evonik Industries AG High Performance Polymers 45764 Marl Germany
PHONE +49 2365 49-9878 **E-MAIL** evonik-hp@evonik.com



EVONIK
INDUSTRIES